

Test Report

Issue Date: 2023-09-11

Intertek Report No. 230911001SHF-001

Test Items, Method and Results:

Test Item: Surface Frictional Properties Using the British Pendulum Tester

Test Method: ASTM E303-22

Test Condition: $23 \pm 2^{\circ}\text{C}$ and $50 \pm 5\%$ relative humidity

Slider: Slider 96

Test Item	Test condition	Test Result
Surface Frictional Properties Using the British Pendulum Tester	Dry condition	British Pendulum Number(BPN): Longitudinal direction: Mean: 93 Min.: 92 Horizontal direction: Mean: 90 Min.: 89

Note:

1. Test surface and direction please refer to Appendix A: Sample Received Photo.

Test Report

Issue Date: 2023-09-11

Intertek Report No. 230911001SHF-001

Test Items, Method and Results:

Test Item: Surface Frictional Properties Using the British Pendulum Tester

Test Method: ASTM E303-22

Test Condition: $23 \pm 2^{\circ}\text{C}$ and $50 \pm 5\%$ relative humidity

Slider: Slider 96

Test Item	Test condition	Test Result
Surface Frictional Properties Using the British Pendulum Tester	Wet condition	British Pendulum Number(BPN):
		Longitudinal direction:
		Mean: 47
		Min.: 45
		Horizontal direction:
		Mean: 45
		Min.: 45

Note:


1. Test surface and direction please refer to Appendix A: Sample Received Photo.

Test Report

Issue Date: 2023-09-11

Intertek Report No. 230911001SHF-001

Appendix A: Sample Received Photo



Revision:

NO.	Date	Changes
230911001SHF-001	2023-09-11	First issue